

# ASTALAC™ ABS KMZ

Acrylonitrile Butadiene Styrene

Marplex Australia Pty. Ltd.

## Message:

ASTALAC™ ABS KMZ is a high melt flow flame retardant ABS which meets the stringent Underwriter's Laboratory UL94 V- 0 flammability test and offers an optimum balance of flame retardancy, impact toughness, product rigidity and mouldability. Typical applications include dishwasher fascia panels and other domestic/industrial electrical casing components.

Note: The letters "UV" or "W" indicate UV additional stabilisation [ ie: ASTALAC™ ABS KMZUV ].

| General Information |                                    |
|---------------------|------------------------------------|
| Additive            | Flame Retardant                    |
| Features            | Flame Retardant                    |
|                     | Good Impact Resistance             |
|                     | Good Moldability                   |
|                     | High Flow                          |
|                     | Medium Rigidity                    |
| Uses                | Electrical/Electronic Applications |
|                     | Industrial Applications            |
|                     | White Goods & Small Appliances     |

| Physical                                         | Nominal Value | Unit              | Test Method             |
|--------------------------------------------------|---------------|-------------------|-------------------------|
| Specific Gravity                                 | 1.16          | g/cm <sup>3</sup> | ASTM D792               |
| Melt Mass-Flow Rate (MFR) (230°C/3.8 kg)         | 5.0           | g/10 min          | ASTM D1238              |
| Molding Shrinkage - Flow (3.00 mm)               | 0.60          | %                 | ASTM D955               |
| Water Absorption (24 hr)                         | 0.25          | %                 | ASTM D570               |
| Hardness                                         | Nominal Value | Unit              | Test Method             |
| Rockwell Hardness (R-Scale)                      | 98            |                   | ASTM D785               |
| Mechanical                                       | Nominal Value | Unit              | Test Method             |
| Tensile Strength <sup>1</sup> (3.20 mm)          | 42.0          | MPa               | ASTM D638               |
| Tensile Elongation <sup>2</sup> (Break, 3.20 mm) | 35            | %                 | ASTM D638               |
| Flexural Modulus <sup>3</sup> (3.20 mm)          | 2300          | MPa               | ASTM D790               |
| Flexural Strength <sup>4</sup> (3.20 mm)         | 70.0          | MPa               | ASTM D790               |
| Impact                                           | Nominal Value | Unit              | Test Method             |
| Notched Izod Impact (3.20 mm)                    | 200           | J/m               | ASTM D256               |
| Thermal                                          | Nominal Value | Unit              | Test Method             |
| Deflection Temperature Under Load                |               |                   | ASTM D648               |
| 1.8 MPa, Unannealed, 3.20 mm                     | 74.0          | °C                |                         |
| 1.8 MPa, Unannealed, 12.7 mm                     | 86.0          | °C                |                         |
| Vicat Softening Temperature                      | 101           | °C                | ASTM D1525 <sup>5</sup> |
| CLTE - Flow                                      | 9.0E-5        | cm/cm/°C          | ASTM D696               |

| Flammability                             | Nominal Value    | Unit               | Test Method       |
|------------------------------------------|------------------|--------------------|-------------------|
| Flame Rating (3.00 mm)                   | V-0              |                    | UL 94             |
| Glow Wire Ignition Temperature (1.60 mm) | 960              | °C                 | AS/NZS 60695.2.12 |
| Injection                                | Nominal Value    | Unit               |                   |
| Drying Temperature                       | 85.0 to 90.0     | °C                 |                   |
| Drying Time                              | 3.0 to 5.0       | hr                 |                   |
| Rear Temperature                         | 195 to 215       | °C                 |                   |
| Middle Temperature                       | 205 to 225       | °C                 |                   |
| Front Temperature                        | 215 to 235       | °C                 |                   |
| Processing (Melt) Temp                   | 210 to 240       | °C                 |                   |
| Mold Temperature                         | 40.0 to 70.0     | °C                 |                   |
| Injection Pressure                       | 60.0 to 140      | MPa                |                   |
| Injection Rate                           | Moderate         |                    |                   |
| Back Pressure                            | 0.100 to 0.500   | MPa                |                   |
| Screw Speed                              | 40 to 60         | rpm                |                   |
| Clamp Tonnage                            | 3.0 to 6.0       | kN/cm <sup>2</sup> |                   |
| NOTE                                     |                  |                    |                   |
| 1.                                       | 5.0 mm/min       |                    |                   |
| 2.                                       | 5.0 mm/min       |                    |                   |
| 3.                                       | 1.3 mm/min       |                    |                   |
| 4.                                       | 1.3 mm/min       |                    |                   |
| 5.                                       | Loading 1 (10 N) |                    |                   |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

