Trademark PE LD2923F

Low Density Polyethylene

Trademark Plastics Corporation

Message:

Trademark PE LD2923F is a Low Density Polyethylene product. It is available in North America. Applications of Trademark PE LD2923F include bags/liners, engineering/industrial parts, film and food contact applications.

Characteristics include:

Antiblock

Clarity

Food Contact Acceptable

Good Processability

General Information

Good Sealability

| Additive | Medium Antiblock | | | |
|---------------------------------------|----------------------------|----------|-------------|--|
| | Medium Slip | | | |
| | | | | |
| Features | Food Contact Acceptable | | | |
| | Good Heat Seal | | | |
| | Good Processability | | | |
| | High Clarity | | | |
| | High Strength | | | |
| | Medium Antiblocking | | | |
| | Medium Slip | | | |
| | | | | |
| Uses | Bags | | | |
| | Film | | | |
| | Heavy-duty Bags | | | |
| | Laundry Bags | | | |
| | Transparent Parts | | | |
| | | | | |
| Agency Ratings | FDA 21 CFR 177.1520(c) 2.1 | | | |
| Physical | Nominal Value | Unit | Test Method | |
| Density | 0.923 | g/cm³ | ASTM D1505 | |
| Melt Mass-Flow Rate (MFR) (190°C/2.16 | | | | |
| kg) | 2.0 | g/10 min | ASTM D1238 | |
| Films | Nominal Value | Unit | Test Method | |
| Film Thickness - Tested | 51 | μm | | |
| Secant Modulus | | | ASTM D882 | |
| 1% Secant, MD : 51 μm, Blown Film | 172 | MPa | | |
| 1% Secant, TD : 51 μm, Blown Film | 200 | MPa | | |
| Tensile Strength | | | ASTM D882 | |
| MD : Break, 51 µm,Blown Film | 24.1 | MPa | | |

| TD : Break, 51 μm,Blown Film | 18.6 | MPa | |
|--------------------------------------|---------------|------|-------------|
| Tensile Elongation | | | ASTM D882 |
| MD : Break, 51 μm,Blown Film | 350 | % | |
| TD : Break, 51 μm,Blown Film | 700 | % | |
| Dart Drop Impact (51 µm, Blown Film) | 100 | g | ASTM D1709 |
| Elmendorf Tear Strength | | | ASTM D1922 |
| MD : 51 µm, Blown Film | 360 | g | |
| TD : 51 µm, Blown Film | 200 | g | |
| Optical | Nominal Value | Unit | Test Method |
| Gloss (45°, 50.8 µm, Blown Film) | 76 | | ASTM D2457 |
| Haze (50.8 µm, Blown Film) | 5.0 | % | ASTM D1003 |
| Extrusion | Nominal Value | Unit | |
| Melt Temperature | 182 to 199 | °C | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

