

Nypol® PA A3 AZL0039 NR318

Polyamide 66

Petropol Industry and Trade of Polymers LTDA

Message:

Nylon 66 in color blue, with good set of mechanical properties, good set of thermal properties. Ideal for injection molding.

General Information				
Appearance	Blue			
Processing Method	Injection Molding			
Resin ID (ISO 1043)	>PA 66<			
Physical	Dry	Conditioned	Unit	Test Method
Specific Gravity	1.14	--	g/cm³	ASTM D792
Molding Shrinkage - Flow	1.5 to 2.0	--	%	ASTM D955
Water Absorption (Equilibrium)	1.3	--	%	ASTM D570
Hardness	Dry	Conditioned	Unit	Test Method
Rockwell Hardness (R-Scale)	120	104		ASTM D785
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Strength	85.0	61.0	MPa	ASTM D638
Tensile Elongation (Break)	30	40	%	ASTM D638
Flexural Modulus	2750	1800	MPa	ASTM D790
Flexural Strength	100	65.0	MPa	ASTM D790
Impact	Dry	Conditioned	Unit	Test Method
Notched Izod Impact	50	60	J/m	ASTM D256
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	65.0	--	°C	ASTM D648
Melting Temperature	250 to 265	--	°C	ASTM D2117
Electrical	Dry	Conditioned	Unit	Test Method
Volume Resistivity	1.0E+14	1.0E+13	ohms·cm	ASTM D257
Injection	Dry	Unit		
Drying Temperature	90.0		°C	
Drying Time	3.0		hr	
Suggested Max Moisture	0.020		%	
Processing (Melt) Temp	260 to 280		°C	
Mold Temperature	70.0 to 100		°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT