

Zhongfa PP ZF-ZR2

Polypropylene

Yuyao Zhongfa Engineering Plastics Co. Ltd.

Message:

Zhongfa PP ZF-ZR2 is a polypropylene material. This product is available in the Asia-Pacific region and is processed by injection molding.

The main features of Zhongfa PP ZF-ZR2 are:

high gloss

chemical resistance

The typical application field of Zhongfa PP ZF-ZR2 is: automotive industry

General Information			
Features	Highlight		
	Good liquidity		
	Good chemical resistance		
Uses	Application in Automobile Field		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.910	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR)	4.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow	1.8	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	50		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	25.0	MPa	ASTM D638
Tensile Elongation (Break)	250	%	ASTM D638
Flexural Modulus	800	MPa	ASTM D790
Flexural Strength	30.0	MPa	ASTM D790
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	110	°C	ASTM D648
Additional Information			
Aging Resistance at 150°C: >400 hrNotched Izod Impact, ASTM D256: 1 kJ/m ² Unnotched Izod Impact, ASTM D256: No Break			
Injection	Nominal Value	Unit	
Drying Temperature	90.0 - 95.0	°C	
Drying Time	2.0 - 3.0	hr	
Processing (Melt) Temp	195 - 225	°C	
Mold Temperature	45.0 - 80.0	°C	
Injection Pressure	60.0 - 90.0	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

