

Celanex® MT2008

Polybutylene Terephthalate

Celanese Corporation

Message:

Celanex MT2008 is a medical grade unreinforced polybutylene terephthalate with a good balance of mechanical properties and processability for use in melt blown applications.

General Information			
Features	Workability, good		
Uses	Medical/nursing supplies		
RoHS Compliance	Contact manufacturer		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.31	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage			
Flow	1.8 - 2.0	%	ASTM D955
Flow direction	1.8 - 2.0	%	ISO 294-4
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	72		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			
Yield, 23°C	55.2	MPa	ASTM D638
Fracture	60.0	MPa	ISO 527-2/1A/5
Tensile Elongation			
Fracture, 23°C	5.0	%	ASTM D638
Fracture	5.0	%	ISO 527-2/1A/5
Flexural Modulus (23°C)	2200	MPa	ISO 178
Flexural Stress (23°C)	80.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	3.1	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	155	°C	ISO 75-2/B
0.45 MPa, annealed	154	°C	ASTM D648
1.8 MPa, not annealed	54.4	°C	ASTM D648
1.8 MPa, not annealed	57.0	°C	ISO 75-2/A
Glass Transition Temperature ¹	60.0	°C	ISO 11357-2
Melting Temperature ²	225	°C	ISO 11357-3, ASTM D3418
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity			

--	1.0E+16	ohms·cm	ASTM D257
--	> 1.0E+15	ohms·cm	IEC 60093
Dielectric Strength			
-- ³	16	kV/mm	ASTM D149
--	15	kV/mm	IEC 60243-1
Dielectric Constant (1 MHz)	3.20		ASTM D150, IEC 60250
Dissipation Factor			
1 MHz	1.0E-3		ASTM D150
1 MHz	0.020		IEC 60250
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	120 - 130	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.020	%	
Hopper Temperature	20.0 - 50.0	°C	
Rear Temperature	230 - 240	°C	
Middle Temperature	235 - 250	°C	
Front Temperature	235 - 250	°C	
Nozzle Temperature	250 - 260	°C	
Processing (Melt) Temp	235 - 260	°C	
Mold Temperature	65.0 - 93.0	°C	
Injection Rate	Moderate-Fast		
Injection instructions			
Manifold Temperature: 250 to 260°CZone 4 Temperature: 240 to 260°CFeed Temperature: 230 to 240°C			
NOTE			
1.	10°C/min		
2.	10°C/min		
3.	Method A (short time)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT