

MAJ'ECO DEP290C

Polypropylene

AD majoris

Message:

MAJ'ECO DEP290C is a vegetal fibre elastomer modified polypropylene compound intended for injection moulding.

MAJ'ECO DEP290C has been developed especially for demanding applications in various engineering sectors.

APPLICATIONS

Product such as:

Boxes

Racks

Technical components

General Information			
Filler / Reinforcement	Natural fiber reinforced material		
Additive	Impact modifier		
Features	Impact modification		
	Updatable resources		
	Recyclable materials		
Uses	Bracket		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	0.905	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	9.0	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	52.0	MPa	ISO 527-2/1
Tensile Stress (Break)	4.50	MPa	ISO 527-2/50
Flexural Modulus ¹	27.0	MPa	ISO 178
Flexural Stress ²	4.70	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	29	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	No Break		ISO 179/1eU
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	4.0	hr	
Processing (Melt) Temp	150 - 180	°C	
Mold Temperature	30.0 - 50.0	°C	
Injection Rate	Moderate		

Injection instructions

Holding pressure: 50 to 70% of the injection pressure

NOTE

- | | |
|----|------------|
| 1. | 2.0 mm/min |
| 2. | 50 mm/min |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

