

TES J-50/20

Polycarbonate
Techmer Engineered Solutions

Message:

TES J-50/20 is a Polycarbonate (PC) product filled with 20% glass fiber. It can be processed by injection molding and is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America.

Characteristics include:

- Flame Rated
- RoHS Compliant
- Creep Resistant
- Fatigue Resistant
- Good Dimensional Stability

General Information			
UL YellowCard	E253782-484572		
Filler / Reinforcement	Glass Fiber,20% Filler by Weight		
Features	Fatigue Resistant		
	Good Creep Resistance		
	Good Dimensional Stability		
	High Heat Resistance		
	High Strength		
RoHS Compliance	RoHS Compliant		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.35	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.30	%	ASTM D955
Water Absorption (24 hr)	0.10	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	80		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	6210	MPa	ASTM D638
Tensile Strength (Break, 23°C)	110	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	3.0	%	ASTM D638
Flexural Modulus (23°C)	5520	MPa	ASTM D790
Flexural Strength (Break, 23°C)	152	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 6.35 mm)	130	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	152	°C	

1.8 MPa, Unannealed	143	°C	
RTI Elec			UL 746
1.47 mm	75.0	°C	
3.05 mm	75.0	°C	
RTI Imp			UL 746
1.47 mm	75.0	°C	
3.05 mm	75.0	°C	
RTI Str			UL 746
1.47 mm	75.0	°C	
3.05 mm	75.0	°C	
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
1.47 mm	V-2		
3.05 mm	V-0		
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	2.0 to 4.0	hr	
Suggested Max Moisture	0.10	%	
Rear Temperature	299 to 316	°C	
Middle Temperature	310 to 343	°C	
Front Temperature	316 to 332	°C	
Nozzle Temperature	310 to 332	°C	
Processing (Melt) Temp	304 to 329	°C	
Mold Temperature	71.1 to 87.8	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT