

TES J-75/30 NAT

Polyamide 6 + PP
Techmer Engineered Solutions

Message:

TES J-75/30 NAT is a Polyamide 6 + PP (Nylon 6+PP) product. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America. Primary characteristic: rohs compliant.

General Information			
RoHS Compliance	RoHS Compliant		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.26	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.30	%	ASTM D955
Water Absorption (24 hr)	0.35	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	121	MPa	ASTM D638
Tensile Elongation (Break)	4.3	%	ASTM D638
Flexural Modulus	7580	MPa	ASTM D790
Flexural Strength	159	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	85	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	166	°C	ASTM D648

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China


WECHAT