

# Hifax TYC 337P

Polyolefin

LyondellBasell Industries

## Message:

Very high flow, impact resistant, mineral filled grade designed for exterior applications

General Information			
Filler / Reinforcement	Mineral		
Features	High Flow		
	High Impact Resistance		
	Medium Rigidity		
Uses	Automotive Applications		
	Automotive Exterior Parts		
	Reinforced Panels		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.990	g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	26	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus	1400	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength			ISO 180/1A
-30°C	5.0	kJ/m <sup>2</sup>	
23°C	40	kJ/m <sup>2</sup>	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT