

Dorlyl PVC GFB 65E

Polyvinyl Chloride

DORLYL S.N.C.

Message:

GFB 65E is a compound that can be presented in : transparent, opaque, colored or with special effects (silver, glitter, fluorescent, pearlescent, ...), with medium impact for use in bottles blow molding up to 0,5 l capacity, according to their characteristics.

General Information			
Features	Impact resistance, good		
	Compliance of Food Exposure		
Uses	Cosmetic Packaging		
	Blow molding applications		
	Bottle		
	Food packaging		
	Medical packaging		
Agency Ratings	European food contact, not rated		
Appearance	Red		
	Clear/transparent		
	Purple		
Forms	Powder		
	Particles		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.36	g/cm ³	ASTM D792
Apparent Density	0.77	g/cm ³	ISO 60
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	77		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break)	41.0	MPa	ISO 527-2
Tensile Strain (Break)	180	%	ISO 527-2
Flexural Modulus (23°C)	2300	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	6.0	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	76.0	°C	ISO 306/B
Additional Information			
Stabilization: TinVolatile Matter, ISO 1269: <0.2%			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

