

Optix® CP-80

Polymethyl Methacrylate Acrylic

Plaskolite West, Inc.

Message:

Optix® CP-80 is a polymethyl methacrylate-acrylic acid product. It can be processed by extrusion and is available in North America or Europe.

Features include:

flame retardant/rated flame

odorless/tasteless channel

high molecular weight

Good processability

insulation

General Information			
UL YellowCard	E167330-100061608		
Features	Good dimensional stability		
	High molecular weight		
	Insulation		
	Impact resistance, good		
	Workability, good		
	Machinable		
	Low liquidity		
	Good chemical resistance		
	Good weather resistance		
	Heat resistance, high		
	The smell is low to none		
	The smell is low to none		
	Definition, high		
Appearance	Available colors		
Forms	Particle		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.19	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/3.8 kg)	2.2	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.50	%	ASTM D955
Water Absorption (24 hr)	0.30	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	87		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3430	MPa	ASTM D638
Tensile Strength	68.9	MPa	ASTM D638
Tensile Elongation (Break)	4.6	%	ASTM D638

Flexural Modulus	3110	MPa	ASTM D790
Flexural Strength	106	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	21	J/m	ASTM D256
Unnotched Izod Impact	310	J/m	ASTM D256
Dart Drop Impact	0.339	J	ASTM D3029
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	91.1	°C	ASTM D648
Vicat Softening Temperature	104	°C	ASTM D1525
CLTE - Flow (-30 to 30°C)	6.1E-5	cm/cm/°C	ASTM D696
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Optical	Nominal Value	Unit	Test Method
Refractive Index	1.490		ASTM D542
Transmittance	92.0	%	ASTM D1003
Haze	1.0	%	ASTM D1003
Additional Information			
Thermal Index, UL-746 ABC: 90°CBurn Rate, ASTM D635: 1.4 in/min			
Injection	Nominal Value	Unit	
Drying Temperature	71.1 - 85.0	°C	
Rear Temperature	204 - 249	°C	
Middle Temperature	210 - 254	°C	
Front Temperature	216 - 260	°C	
Nozzle Temperature	210 - 260	°C	
Processing (Melt) Temp	210 - 254	°C	
Mold Temperature	48.9 - 93.3	°C	
Injection instructions			
Heated Manifold: 410-490°FHeated Drop (Sprue): 410-490°F			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT