

REVOLVE® M-762

Polyethylene

Matrix Polymers

Message:

Revolve M-762 is a fully formulated black rotomoulding resin suitable in applications where stiffness is a requirement. This grade presents excellent stiffness, good impact strength and toughness.

General Information			
Additive	UV Stabilizer		
Features	Good Impact Resistance		
	Good Moldability		
	Good Toughness		
	High Hardness		
	High Stiffness		
Appearance	Black		
Forms	Powder		
Processing Method	Rotational Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.939	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR)	3.2	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	21.0	MPa	ISO 527-2/50
Flexural Modulus ¹	800	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Low Temperature Impact - ARM (3.00 mm)	95.0	J	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	47.0	°C	ISO 75-2/A
NOTE			
1.	1.3 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT