

Alpha TPR AG005-4B NATURAL

Styrenic Thermoplastic Elastomer

AlphaGary

Message:

A STYRENIC-BASED THERMOPLASTIC ELASTOMER INTENDED FOR MEMBRANE HORN, FLOATING HORN, AND DRIVER SIDE AIRBAG COVER. THIS COMPOUND HAS EXCELLENT PROCESSABILITY, FLEXIBILITY, DURABILITY, AND LOW TEMPERATURE PROPERTIES.

General Information			
Features	Durable		
	Good Flexibility		
	Good Processability		
Uses	Automotive Applications		
Agency Ratings	FDA Unspecified Rating		
RoHS Compliance	Contact Manufacturer		
Appearance	Natural Color		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.878 to 0.918	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	2.5	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore D	39 to 45		
Shore D, 5 sec	30 to 36		
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus (1.91 mm)	179	MPa	ASTM D790
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (1.91 mm)	11.7	MPa	ASTM D412
Tensile Elongation (Break, 1.91 mm)	600	%	ASTM D412

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT