Echo® RPC20G BK

Polypropylene Homopolymer

Ravago Manufacturing Americas, LLC

Message:

Echo® RPC20G BK is a Polypropylene Homopolymer (PP Homopolymer) product filled with 20% glass fiber. It is available in North America. Characteristics include:

Eco-Friendly/Green

Homopolymer

| General Information | | | |
|---|----------------------------------|----------|-------------|
| Filler / Reinforcement | Glass Fiber,20% Filler by Weight | | |
| Recycled Content | Yes | | |
| Features | Homopolymer | | |
| Appearance | Black | | |
| Forms | Pellets | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 1.09 | g/cm³ | ASTM D792 |
| Melt Mass-Flow Rate (MFR) (230°C/2.16 kg) | 6.0 | g/10 min | ASTM D1238 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength | 59.0 | МРа | ASTM D638 |
| Tensile Elongation (Yield, 23°C) | 3.0 | % | ASTM D638 |
| Flexural Modulus (23°C) | 4250 | МРа | ASTM D790 |
| Impact | Nominal Value | Unit | Test Method |
| Notched Izod Impact (23°C, 3.18 mm) | 91 | J/m | ASTM D256 |
| Thermal | Nominal Value | Unit | Test Method |
| Deflection Temperature Under Load (1.8 MPa, Unannealed) | 145 | °C | ASTM D648 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

