Spartech Polycom SC1-1210

Acrylonitrile Butadiene Styrene

Spartech Polycom

Message:

Spartech SC1-1210 is a medium viscosity ABS resin for injection molding that features 10% glass fiber reinforcement. It is heat stabilized and lubricated for good processing characteristics, and it exhibits good impact and chemical resistance. With the addition of the glass, this grade has increased strength and modulus properties.

With the benefit of low moisture absorption, ABS can be used in a variety of environments. Being a very versatile product, SC1-1210 can be used for industrial, transportation, sporting goods and electrical/electronic applications.

General Information				
Filler / Reinforcement	Glass fiber reinforced material, 10% filler by weight			
Additive	heat stabilizer			
	Lubricant			
Features	Low hygroscopicity			
	High strength			
	Impact resistance, good			
	Workability, good			
	Good chemical resistance			
	Thermal Stability			
	Thermal stability, good			
	Lubrication			
	Medium viscosity			
Uses	Electrical/Electronic Applications			
	Industrial application			
	Application in Automobile Field			
	Sporting goods			
Appearance	Available colors			
	Natural color			
Forms	Particle			
Processing Method	Injection molding			
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength (Yield, 23°C)	41.4	MPa	ASTM D638	
Flexural Modulus (23°C)	3450	MPa	ASTM D790	
Flexural Strength (23°C)	65.5	MPa	ASTM D790	
Impact	Nominal Value	Unit	Test Method	
Notched Izod Impact (23°C)	85	J/m	ASTM D256	

Injection	Nominal Value	Unit
Drying Temperature	87.8	°C
Drying Time	2.0 - 4.0	hr
Rear Temperature	210 - 240	°C
Middle Temperature	215 - 245	°C
Front Temperature	220 - 250	°C
Nozzle Temperature	218 - 260	°C
Processing (Melt) Temp	218 - 260	°C
Mold Temperature	43.3 - 65.6	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

