

HAIPLEN H10 T6

Polypropylene Homopolymer

Taro Plast S.p.A.

Message:

Polypropylene homopolymer 30% talcum filled, low flow, high stiffness.

General Information			
Filler / Reinforcement	Talc filler, 30% filler by weight		
Features	Rigidity, high		
	Homopolymer		
	Low liquidity		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.14	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	2.0	g/10 min	ISO 1133
Molding Shrinkage			Internal method
Vertical flow direction	1.1	%	Internal method
Flow direction	1.1	%	Internal method
Granule Humidity ¹	0.050	%	
Reinforcement Content ² (550°C)	30	%	ISO 3451
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2700	MPa	ISO 527-2/1
Tensile Stress (Yield)	30.0	MPa	ISO 527-2/50
Tensile Strain (Break)	30	%	ISO 527-2/50
Flexural Modulus ³	2500	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	35	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	80.0	°C	ISO 75-2/A
Vicat Softening Temperature			
--	155	°C	ISO 306/A50
--	95.0	°C	ISO 306/B50
Ball Pressure Test (125°C)	Pass		IEC 60695-10-2
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index (Solution A)	> 600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Burning Rate ⁴ (2.00 mm)	< 100	mm/min	ISO 3795
Flame Rating (1.60 mm)	HB		UL 94

Oxygen Index	21	%	ASTM D2863
Injection	Nominal Value	Unit	
Processing (Melt) Temp	190 - 220	°C	
Mold Temperature	50.0 - 70.0	°C	
Injection Rate	Fast		
Injection instructions			
Pre-heat Temperature: 70 to 80°CPre-heat Time: 1 hr			
NOTE			
1.	TARO 002		
2.	1 hr		
3.	1.0 mm/min		
4.	US FMVSS302		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

