

QR Resin QR-9046-GF15

Polyamide 46

QTR, Inc.

Message:

QR Resin QR-9046-GF15 is a Polyamide 46 (Nylon 46) product filled with 15% glass fiber. It is available in North America.

Characteristics include:

Chemical Resistant

Good Stiffness

Heat Resistant

Heat Stabilizer

General Information			
Filler / Reinforcement	Glass Fiber,15% Filler by Weight		
Additive	Heat Stabilizer		
Features	Good Chemical Resistance		
	Good Stiffness		
	Good Strength		
	Heat Stabilized		
	High Heat Resistance		
	Oil Resistant		
Appearance	Black		
	Colors Available		
	Natural Color		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.30	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.60 to 0.90	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	5800	MPa	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus	5500	MPa	ASTM D790
Flexural Strength (Break)	220	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	85	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	254	°C	ASTM D648
Melting Temperature	304	°C	
Injection	Nominal Value	Unit	
Drying Temperature	85.0	°C	

Drying Time	2.0 to 4.0	hr
Drying Time, Maximum	4.0	hr
Rear Temperature	282 to 293	°C
Middle Temperature	293 to 310	°C
Front Temperature	299 to 310	°C
Nozzle Temperature	304	°C
Processing (Melt) Temp	304 to 313	°C
Mold Temperature	82.2 to 149	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

