

Delrin® FG500P NC010

ACETAL RESIN

DuPont Performance Polymers

Message:

Medium Viscosity Acetal Homopolymer Developed for Food Contact Applications

General Information			
UL YellowCard	E41938-100907458		
Additive	Lubricant		
	Mold Release		
Features	Lubricated		
Agency Ratings	UL Unspecified Rating		
Forms	Pellets		
Processing Method	Injection Molding		
Multi-Point Data	Isothermal Stress vs. Strain (ISO 11403-1)		
	Secant Modulus vs. Strain (ISO 11403-1)		
	Shear Modulus vs. Temperature (ISO 11403-1)		
	Shear Stress vs. Shear Rate (ISO 11403-1)		
	Viscosity vs. Shear Rate (ISO 11403-2)		
Part Marking Code (ISO 11469)	>POM<		
Resin ID (ISO 1043)	POM		
Physical	Nominal Value	Unit	Test Method
Density	1.42	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	15	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (190°C/2.16 kg)	13.0	cm³/10min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow	1.9	%	
Flow	2.0	%	
Water Absorption			ISO 62
23°C, 24 hr, 2.00 mm	1.4	%	
Equilibrium, 23°C, 2.00 mm, 50% RH	0.30	%	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			ISO 2039-2
M-Scale	92		
R-Scale	120		
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3100	MPa	ISO 527-2

Tensile Stress (Yield)	70.0	MPa	ISO 527-2
Tensile Strain (Yield)	17	%	ISO 527-2
Nominal Tensile Strain at Break	30	%	ISO 527-2
Tensile Creep Modulus			ISO 899-1
1 hr	2800	MPa	
1000 hr	1600	MPa	
Flexural Modulus	2900	MPa	ISO 178
Flexural Stress (3.5% Strain)	80.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-40°C	8.0	kJ/m ²	
-30°C	8.0	kJ/m ²	
23°C	9.0	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	240	kJ/m ²	
23°C	300	kJ/m ²	
Notched Izod Impact Strength			ISO 180/1A
-30°C	8.0	kJ/m ²	
23°C	9.0	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	158	°C	ISO 75-2/B
1.8 MPa, Unannealed	94.0	°C	ISO 75-2/A
Vicat Softening Temperature	155	°C	ISO 306/B50
Melting Temperature ¹	178	°C	ISO 11357-3
CLTE			ISO 11359-2
Flow	1.1E-4	cm/cm/°C	
Transverse	1.1E-4	cm/cm/°C	
Flammability	Nominal Value		Test Method
Flammability Classification			IEC 60695-11-10, -20
0.800 mm	HB		
1.50 mm	HB		
NOTE			
1.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

