

CRYSTALADD® HM-237

Low Density Polyethylene
Ravago Manufacturing Americas, LLC

Message:

NUCLEATOR MASTERBATCH

HM-237 is an additive concentrate containing a highly efficient Nucleator. Nucleation in LLDPE can improve film properties, clarity, barrier and yield rates. In blow molding for PE, HM-237 can reduce cycle time and achieve better control over shrinkage characteristics. In injection molding applications the nucleator will provide faster cycle times, lower shrinkage and higher barrier properties.

Key Features:

Designed to be added to polyethylene film, extrusion, blow molding and injection molding resins.

Improved Clarity in Films, bottles and injection molded articles

Uniform concentration of additives in concentrate form.

Masterbatch pellet form for ease of addition and feeding into extrusion equipment

Directions for Use:

HM-237 is added to HDPE, LDPE or LLDPE at 2.5% to achieve improved crystallization for faster cooling, lower warpage especially between different colors. Achieve more uniform crystal sizes as the PE cools for improved gloss and barrier properties along with excellent clarity.

Note: Effectiveness reduced in LDPE with molecular weights resulting in < 2.0 MI or high LCB.

FDA Compliance:

The components of this product are compliant with FDA requirements up to 9% LD by weight. Please consult with the FDA regulations for specific application requirements.

This product has a Drug Master File (DMF) listing.

General Information	
Uses	Masterbatch
Agency Ratings	DMF Unspecified Rating
	FDA Unspecified Rating
Forms	Pellets
Processing Method	Blow Molding
	Extrusion
	Film Extrusion
	Injection Molding

Physical	Nominal Value	Unit	Test Method
Density	0.920	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	3.9	g/10 min	ASTM D1238
Additional Information	Nominal Value	Unit	Test Method
Nucleating Agent	4.0	%	Internal Method
Polymer Base	LDPE		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

