

ALCUDIA® EBA PA-1906

Ethylene Butyl Acrylate Copolymer
REPSOL

Message:

BA copolymer ALCUDIA® PA-1906 is a copolymer suitable for blown film applications where good processability, flexibility and good mechanical properties are required. The butyl acrylate content is 19%. It contains antioxidant additives.
EBA ALCUDIA® PA-1906 fulfils the food contact regulations in most countries. For further information or certificates, contact our Customer Service Offices.

APPLICATIONS

Film extrusion
Stretch hood film

Recommended melt temperature range is 160 to 180°C. EBA copolymers exhibit excellent thermal stability, which allows higher processing temperatures if needed. Processing characteristics of PA-1906 are similar to LDPE and conventional Polyethylene extruders are recommended.

General Information			
Additive	Antioxidation		
Features	Antioxidation		
	Workability, good		
	Good flexibility		
Uses	Films		
	Stretch winding		
Processing Method	Blow film		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	0.925	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.60	g/10 min	ISO 1133
n-Butyl Acrylate Content	19.0	wt%	
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	100	µm	
Tensile Stress			ISO 527-3
MD: Broken, 100 µm, blown film	25.0	MPa	ISO 527-3
TD: Broken, 100 µm, blown film	28.0	MPa	ISO 527-3
Tensile Elongation			ISO 527-3
MD: Broken, 100 µm, blown film	800	%	ISO 527-3
TD: Broken, 100 µm, blown film	850	%	ISO 527-3
Dart Drop Impact (100 µm, Blown Film)	1300	g	ISO 7765-1
Elmendorf Tear Strength ¹			ISO 6483-2
MD : 100.0 µm	42.0	kN/m	ISO 6483-2
TD : 100.0 µm	47.0	kN/m	ISO 6483-2
Thermal	Nominal Value	Unit	
Melting Temperature	92.0	°C	

Additional Information

Data taken from 100 µm thickness film, blow up ratio 1:2.5, frost line height 50 cm.

Extrusion	Nominal Value	Unit
Melt Temperature	160 - 180	°C

NOTE

1. Blown Film

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

