

Durethan® BKV 35 H2.0 901510

Polyamide 6

LANXESS Corporation

Message:

PA 6, 35 % glass fibers, injection molding, heat-aging stabilized

General Information				
UL YellowCard		E245249-473594		
Filler / Reinforcement		Glass fiber reinforced material, 35% filler by weight		
Additive		heat stabilizer		
Features		Thermal Stability		
Processing Method		Injection molding		
Physical	Dry	Conditioned	Unit	Test Method
Density (23°C)	1.41	--	g/cm ³	ISO 1183
Apparent Density	0.70	--	g/cm ³	ISO 60
Molding Shrinkage				ISO 2577
Vertical flow direction: 280°C, 2.00mm ¹	0.70	--	%	ISO 2577
Vertical flow direction: 120°C, 4 hours, 2.00mm ²	0.14	--	%	ISO 2577
Flow direction: 280°C, 2.00mm ³	0.23	--	%	ISO 2577
Flow direction: 120°C, 4 hours, 2.00mm ⁴	0.070	--	%	ISO 2577
Water Absorption				ISO 62
Saturated, 23°C	6.5	--	%	ISO 62
Equilibrium, 23°C, 50% RH	1.9	--	%	ISO 62
Hardness	Dry	Conditioned	Unit	Test Method
Ball Indentation Hardness	230	120	MPa	ISO 2039-1
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	10700	6800	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	180	110	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	3.0	5.0	%	ISO 527-2/5
Tensile Creep Modulus				ISO 899-1
1 hr	--	6000	MPa	ISO 899-1
1000 hr	--	4900	MPa	ISO 899-1
Flexural Modulus ⁵ (23°C)	10700	5900	MPa	ISO 178/A
Flexural Stress				ISO 178/A
3.5% strain, 23°C	280	160	MPa	ISO 178/A
23°C ⁶	290	180	MPa	ISO 178/A

Flexural Strain at Flexural Strength ⁷ (23°C)	4.0	5.0	%	ISO 178/A
Burning Behavior ⁸ (> 1.00 mm)	passed	--		ISO 3795
ISO Shortname	PA 6, GHR, 14-110, GF35	--		ISO 1874
Residual Moisture Content	0.030 - 0.12		%	Karl Fisher
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	< 10	10	kJ/m ²	ISO 179/1eA
23°C	12	20	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	70	70	kJ/m ²	ISO 179/1eU
23°C	80	90	kJ/m ²	ISO 179/1eU
Notched Izod Impact				ISO 180/1A
-30°C	< 10	10	kJ/m ²	ISO 180/1A
23°C	15	20	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength				ISO 180/1U
-30°C	70	65	kJ/m ²	ISO 180/1U
23°C	75	85	kJ/m ²	ISO 180/1U
Multi-Axial Instrumented Impact Energy				ISO 6603-2
-30°C	3.30	--	J	ISO 6603-2
23°C	3.90	--	J	ISO 6603-2
Multi-Axial Instrumented Impact Peak Force				ISO 6603-2
-30°C	945	--	N	ISO 6603-2
23°C	1060	--	N	ISO 6603-2
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, not annealed	215	--	°C	ISO 75-2/B
1.8 MPa, not annealed	205	--	°C	ISO 75-2/A
8.0 MPa, not annealed	150	--	°C	ISO 75-2/C
Vicat Softening Temperature				
--	200	--	°C	ISO 306/B50
--	> 200	--	°C	ISO 306/B120
Melting Temperature ⁹	222	--	°C	ISO 11357-3
Linear thermal expansion coefficient				ISO 11359-2
Flow: 23 to 55°C	2.0E-5	--	cm/cm/°C	ISO 11359-2
Lateral: 23 to 55°C	8.0E-5	--	cm/cm/°C	ISO 11359-2

Electrical	Dry	Conditioned	Unit	Test Method
Comparative Tracking Index (Solution A)	475	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
1.60 mm	HB	--		UL 94
3.20 mm	HB	--		UL 94
Glow Wire Flammability Index (2.00 mm)	650	--	°C	IEC 60695-2-12
Oxygen Index ¹⁰	23	--	%	ISO 4589-2
Injection	Dry	Unit	Test Method	
Drying Temperature - Dry Air Dryer	80.0		°C	
Drying Time - Dry Air Dryer	2.0 - 6.0		hr	
Processing (Melt) Temp	270 - 290		°C	
Mold Temperature	80.0 - 120		°C	
NOTE				

1. 60x60x2mm, 80°C MT, 600 bar

2. 60x60x2mm

3. 60x60x2mm, 80°C MT, 600 bar

4. 60x60x2mm

5. 2.0 mm/min

6. 2.0 mm/min

7. 2 mm/min

8. US-FMVSS302

9. 10°C/min

10. Procedure A

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT