

Kumho ABS HU650ZW

Acrylonitrile Butadiene Styrene
Korea Kumho Petrochemical Co., Ltd.

Message:

Features: Low gloss, High heat resistance, weather stable
Applications: Injected paroducts demanding for heat resistance and low gloss

General Information			
Features	Good Weather Resistance		
	High Heat Resistance		
	Low Gloss		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.05	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR)			
200°C/21.6 kg	5.0	g/10 min	ASTM D1238
220°C/10.0 kg	3.5	g/10 min	ASTM D1238
220°C/10.0 kg	4.0	g/10 min	ISO 1133
Molding Shrinkage			
Flow	0.50 to 0.80	%	ASTM D955
--	0.50 to 0.80	%	ISO 294-4
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	105		ASTM D785, ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			
Yield	47.1	MPa	ASTM D638
Yield	45.0	MPa	ISO 527-2
Tensile Elongation			
Yield	15	%	ASTM D638
Break	20	%	ISO 527-2
Flexural Modulus			
--	2210	MPa	ASTM D790
--	2300	MPa	ISO 178
Flexural Stress			
--	67.0	MPa	ISO 178
Yield	63.7	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	19	kJ/m ²	ISO 179/1eA
Notched Izod Impact			

23°C, 3.20 mm	210	J/m	ASTM D256
23°C, 6.40 mm	180	J/m	ASTM D256
23°C	18	kJ/m²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	112	°C	ISO 75-2/B
1.8 MPa, Unannealed	104	°C	ASTM D648
1.8 MPa, Unannealed	99.0	°C	ISO 75-2/A
Vicat Softening Temperature	114	°C	ISO 306/B50, ASTM D1525 1
Flammability	Nominal Value	Test Method	
Flame Rating (1.60 mm)	HB	UL 94	
NOTE			

1. Rate A (50°C/h), Loading 2 (50 N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

