

Neoflex™ 7075

Thermoplastic Elastomer

Zylog Plastalloys Pvt. Ltd.

Message:

Neoflex 7075 is a soft, Thermoplastic Elastomer intended for Injection, Blow Moulding and Extrusion applications.

General Information	
Features	Soft
Uses	Blow molding applications
Processing Method	Blow molding
	Extrusion
	Injection molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity ¹	1.15	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 5 sec, 23°C)	76		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ² (100% Strain)	4.41	MPa	ASTM D412
Tensile Strength ³ (Break)	6.37	MPa	ASTM D412
Tensile Elongation ⁴ (Break)	380	%	ASTM D412
Tear Strength ⁵	24.5	kN/m	ASTM D624
Compression Set (70°C, 22 hr)	85	%	ASTM D395B

NOTE	
1.	23°C
2.	C mold, 500 mm/min
3.	C mold, 500 mm/min
4.	C mold, 500 mm/min
5.	C mold, 500 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT