

Anjaflam® 150-UV/FR/GF10

Polycarbonate
Almaak International GmbH

Message:

Anjaflam® 150-UV/FR/GF10 is a Polycarbonate (PC) material filled with 10% glass fiber. It is available in Europe for injection molding.
Important attributes of Anjaflam® 150-UV/FR/GF10 are:
Flame Rated
Flame Retardant
Good UV Resistance
UV Stabilized

General Information			
Filler / Reinforcement	Glass Fiber,10% Filler by Weight		
Additive	Flame Retardant		
	UV Stabilizer		
Features	Flame Retardant		
	Good UV Resistance		
Appearance	Natural Color		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.28	g/cm³	ISO 1183
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	8.00	cm³/10min	ISO 1133
Water Absorption			ISO 62
23°C, 24 hr	0.30	%	
Equilibrium, 23°C, 50% RH	0.13	%	
Relative Viscosity	56.0		ISO 1628
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	4000	MPa	ISO 527-2/1
Tensile Stress (Break)	75.0	MPa	ISO 527-2/5
Tensile Strain (Break)	5.0	%	ISO 527-2/5
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	8.0	kJ/m²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	70	kJ/m²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	142	°C	ISO 75-2/B
1.8 MPa, Unannealed	135	°C	ISO 75-2/A
Glass Transition Temperature	148	°C	DSC
Vicat Softening Temperature	145	°C	ISO 306/B50

Electrical	Nominal Value	Unit	Test Method
Electric Strength (1.50 mm)	30	kV/mm	IEC 60243-1
Comparative Tracking Index (1.50 mm)	175	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	V-0		UL 94
Glow Wire Flammability Index (4.00 mm)	960	°C	IEC 60695-2-12
Injection	Nominal Value	Unit	
Drying Temperature	120	°C	
Drying Time	2.0 to 5.0	hr	
Suggested Max Moisture	0.020	%	
Processing (Melt) Temp	280 to 320	°C	
Mold Temperature	85.0 to 120	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

