

# Kemcor LD 1108

Low Density Polyethylene

Qenos Pty Ltd

Message:

This resin in manufactured to conform to the requirements for unrestricted food contact of AS 2070 Part 1 (1992).

General Information			
Additive	High Antiblock		
	Low Slip		
Features	Good Processability		
	High Antiblocking		
	High Impact Resistance		
	Low Slip		
Uses	Film		
	Laminates		
	Liners		
	Packaging		
Forms	Pellets		
Processing Method	Film Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	0.924	g/cm <sup>3</sup>	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.30	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D882
MD : Break	22.0	MPa	
TD : Break	20.0	MPa	
Dart Drop Impact	320	g	ASTM D1709
Optical	Nominal Value	Unit	Test Method
Haze	11	%	ASTM D1003

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

