

Mecoline IS RDX 1232 F

Thermoplastic

Melos GmbH

Message:

This compound with extra low temperature resistance and extra oil resistance is classified as hazard level 4 identification code M. It is an excellent choice for compact wiring systems, where a reduced wall thickness results in space and weight savings

General Information			
Additive	Flame Retardant		
Features	Flame Retardant		
	Good Abrasion Resistance		
	Good Flexibility		
	Halogen Free		
	High Heat Resistance		
	Irradiation Crosslinkable		
	Low Smoke Emission		
	Low Temperature Flexibility		
	Low Temperature Resistant		
	Oil Resistant		
Uses	Cable Jacketing		
	Insulation		
	Wire & Cable Applications		
Agency Ratings	EN 50306-1 S2		
	EN 50306-2		
RoHS Compliance	RoHS Compliant		
Forms	Pellets		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	1.40	g/cm ³	ISO 1183/A
Melt Mass-Flow Rate (MFR) (190°C/10.0 kg)	3.9	g/10 min	ISO 1133
Water Absorption - after 168h at 70°C	< 15.0	mg/cm ²	
pH	> 4.5		IEC 60754-2
Shrinkage - 1h at 120°C	< 2.0	%	IEC 811-1-3
Hot Pressure Test - penetration 4h at 140°C	< 50	%	DIN VDE 0472
Hot Set ¹			IEC 540
Elongation under load	< 60	%	

Residual elongation	< 10	%	
Temperature Index	250	°C	ASTM D2863
Conductivity	< 4.00	μS/mm	EN 50267-2-2
Halogen Content	0	%	IEC 754-1
Toxicity	2.60		EN 50305
Head Temperature	155 to 165	°C	
Extruder Screw L/D Ratio	>25.0:1.0		
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	50		ISO 7619
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress			IEC 811-1-1
-- ²	> 16.0	MPa	
-- ³	> 15.0	MPa	
Tensile Strain			
Break ⁴	> 150	%	IEC 811-1-1
Break ⁵	> 200	%	IEC 811-1-1
Break, -40°C	> 30	%	IEC 811-1-4
Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength in Air (120°C, 240 hr)	< 25	%	IEC 811-1-2
Change in Tensile Strain at Break in Air (120°C, 240 hr)	< 25	%	IEC 811-1-2
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity			IEC 60093
23°C	1.0E+15	ohms·cm	
90°C	< 1.0E+12	ohms·cm	
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	32	%	ASTM D2863
Extrusion	Nominal Value	Unit	
Cylinder Zone 1 Temp.	130 to 140	°C	
Cylinder Zone 2 Temp.	140 to 150	°C	
Cylinder Zone 3 Temp.	150 to 160	°C	
Cylinder Zone 4 Temp.	155 to 165	°C	
Cylinder Zone 5 Temp.	155 to 165	°C	
Adapter Temperature	155 to 165	°C	
Die Temperature	160 to 170	°C	
NOTE			
1.	at 200°C/15min/0.2 MPa		
2.	After crosslinking		
3.	Before crosslinking		
4.	After crosslinking		
5.	Before crosslinking		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

