HiFill® LDPE 0098 S LE

Low Density Polyethylene

Techmer Engineered Solutions

Message:

HiFill® LDPE 0098 S LE is a Low Density Polyethylene product filled with filler. It can be processed by injection molding and is available in North America. Typical application: Food Contact Applications.

| General Information | | | |
|---|------------------------|----------|-------------|
| Filler / Reinforcement | Filler | | |
| Features | Low Extractables | | |
| | Metal Detectable | | |
| | | | |
| Agency Ratings | FDA Unspecified Rating | | |
| Appearance | Colors Available | | |
| Forms | Pellets | | |
| Processing Method | Injection Molding | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 0.978 | g/cm³ | ASTM D792 |
| Melt Mass-Flow Rate (MFR) (190°C/2.16 | | | |
| kg) | 8.0 | g/10 min | ASTM D1238 |
| Molding Shrinkage - Flow (3.18 mm) | 1.9 | % | ASTM D955 |
| Water Absorption (24 hr) | 0.050 | % | ASTM D570 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength (Yield) | 10.3 | MPa | ASTM D638 |
| Tensile Elongation (Yield) | 80 | % | ASTM D638 |
| Flexural Modulus | 276 | MPa | ASTM D790 |
| Flexural Strength | 15.2 | MPa | ASTM D790 |
| Impact | Nominal Value | Unit | Test Method |
| Notched Izod Impact (23°C, 3.18 mm) | 270 | J/m | ASTM D256 |
| Thermal | Nominal Value | Unit | Test Method |
| Deflection Temperature Under Load (0.45 | 07.0 | | |
| MPa, Unannealed) | 87.8 | °C | ASTM D648 |
| CLTE - Flow | 3.4E-5 | cm/cm/°C | ASTM D696 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519 Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

