Jackdaw PP EX10BK6537

Polypropylene

Jackdaw Polymers

Message:

Jackdaw PP EX10BK6537 is a Polypropylene product filled with 20% glass fiber. It is available in Europe.

Characteristics include:

Flame Rated

Flame Retardant

| General Information | | | | |
|--------------------------------------|-----------------------------|----------------------------------|-----------------------|--|
| Filler / Reinforcement | Glass Fiber,20% Filler by \ | Glass Fiber,20% Filler by Weight | | |
| Additive | Flame Retardant | Flame Retardant | | |
| Features | Flame Retardant | | | |
| Appearance | Black | | | |
| Physical | Nominal Value | Unit | Test Method | |
| Specific Gravity | 1.07 | g/cm³ | ASTM D792, ISO 1183 | |
| Molding Shrinkage | 0.30 | % | Internal Method | |
| Mechanical | Nominal Value | Unit | Test Method | |
| Tensile Strength (Break) | 80.0 | MPa | ASTM D638, ISO 527-2 | |
| Tensile Elongation (Break) | 3.0 | % | ASTM D638, ISO 527-2 | |
| Flexural Modulus | 4000 | MPa | ASTM D790, ISO 178 | |
| Flexural Stress | | | | |
| | 100 | MPa | ISO 178 | |
| Break | 100 | MPa | ASTM D790 | |
| Impact | Nominal Value | Unit | Test Method | |
| Notched Izod Impact Strength | 9.0 | kJ/m² | ISO 180 | |
| Thermal | Nominal Value | Unit | Test Method | |
| Deflection Temperature Under Load (1 | 1.8 | | | |
| MPa, Unannealed) | 135 | °C | ASTM D648, ISO 75-2/A | |
| Peak Melting Temperature | 175 | °C | ASTM D2117, ISO 1218 | |
| Flammability | Nominal Value | | Test Method | |
| Flame Rating | V-0 | | UL 94 | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

