NuSil MED-6400

Silicone

NuSil Technology

Message:

NuSil Technology's unrestricted materials may be considered for long-term implant applications (greater than 29 days).

"Dispersion" is a term used to describe a silicone elastomer system that is suspended or dispersed in a solvent carrier. It is a complex solution that contains silicone polymers of various molecular weights and reinforcing fi llers. The substituent groups comprising the polymer back bone structure may consist of the following: Polydimethylsiloxane, Dimethyl Diphenyl copolymer, and Fluoro homo polymer or copolymer. Silicone dispersions typically have low viscosities, which is beneficial for applications wherein a thin fi Im coating is needed, and they can easily be used in dipping and spraying processes. NuSil uses a variety of solvents to disperse silicones, such as xylene, tert butyl acetate, heptane, hexane, acetone and naphtha. Comments: 1.43 R.I. IN XYLENE

| General Information | | |
|--------------------------------|---------------------------------|-------|
| Filler / Reinforcement | Filler | |
| Features | Low Viscosity | |
| Uses | Coating Applications | |
| | Medical/Healthcare Applications | |
| | | |
| Agency Ratings | USP Class VI | |
| Forms | Dispersion | |
| Processing Method | Dip Coating | |
| | Spraying | |
| | | |
| Mechanical | Nominal Value | Unit |
| Tensile Strength (300% Strain) | 2.41 | МРа |
| Optical | Nominal Value | |
| Refractive Index | 1.430 | |
| Thermoset | Nominal Value | Unit |
| Thermoset Components | | |
| Part A | Mix Ratio by Weight: 1.0 | |
| Part B | Mix Ratio by Weight: 1.0 | |
| Additional Information | Nominal Value | Unit |
| Cure System | Platinum | |
| Uncured Properties | Nominal Value | Unit |
| Density | 1.08 | g/cm³ |
| Viscosity | 0.60 | Pa·s |
| Curing Time ¹ | 3.5 | hr |
| Pot Life (25°C) | 1400 | min |
| Cured Properties | Nominal Value | Unit |
| Shore Hardness (Shore A) | 30 | |
| Tensile Strength | 10.3 | MPa |
| Tensile Elongation at Break | 780 | % |

| Tear Strength | 26.3 | kN/m | |
|---------------|----------------------------------|------|--|
| NOTE | | | |
| 1. | 30m/25°C + 45m/75° 135m/150°C | 2 + | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

