# Calprene® H6140

Styrene Ethylene Butylene Styrene Block Copolymer

#### **Dynasol Elastomers**

#### Message:

Calprene H6140 is a 69/31 ethylene-butylene/styrene thermoplastic copolymer, polymerized in solution and having a linear structure with excellent ozone resistance.

This product is available in:

CH 6140 porous pellet

CH 6140 P powder form dusted WITH amorphous silica

CH 6140 PH powder form WITHOUT any dusting agent

APPLICATIONS:

Compounding

Plastic modification

General Information			
Features	Copolymer		
	Linear Polymer Structure		
	Ozone Resistant		
	Porous		
Uses	Compounding		
	Plastics Modification		
Forms	Pellets		
	Powder		
Processing Method	Compounding		
Physical	Nominal Value	Unit	Test Method
Color - Hunterlab	< 3.0		ASTM E313
Solution Viscosity - 5.23% in toluene <sup>1</sup>	30	cSt	
Styrene Content <sup>2</sup>	31	%	
Volatile Matter	< 0.50	%	ASTM D5668
Brookfield Viscosity - 10% <sup>3</sup> (25°C)	400	mPa∙s	
Saturation <sup>4</sup>	> 99	%	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	75		ASTM D2240
NOTE			
1.	MA 04-3-003		
2.	MA 04-3-062		
3.	MA 04-3-064		
4.	NMR		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any

### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



Page 2