

Spartech Polycom X05041

Polypropylene
Spartech Polycom

Message:

Spartech Polycom X05041 is a polypropylene product, which contains 25% talc filler. It is available in North America.
Features include:
Impact modification
Good stiffness

General Information			
Filler / Reinforcement	Talc filler, 25% filler by weight		
Additive	Impact modifier		
Features	Impact modification		
	Rigid, good		
Appearance	Natural color		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.11	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	19	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.18 mm)	1.7	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 23°C)	27.6	MPa	ASTM D638
Tensile Elongation			ASTM D638
Yield, 23°C	7.0	%	ASTM D638
Fracture, 23°C	200	%	ASTM D638
Flexural Modulus			ASTM D790
Secant: 23°C	1720	MPa	ASTM D790
Tangent: 23°C	2590	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	64	J/m	ASTM D256
Dart Drop Impact (23°C)	8.81	J	ASTM D3029
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	118	°C	ASTM D648
1.8 MPa, not annealed	60.0	°C	ASTM D648

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

