

Medalist® MD-100

Thermoplastic Elastomer

Teknor Apex Company

Message:

This compound is designed for medical and healthcare applications requiring an ultra-soft, gel like material.

General Information			
Uses	Drug		
	Medical/nursing supplies		
Agency Ratings	ISO 10993 Part 5		
Appearance	Clear/transparent		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.870	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (125°C/2.16 kg)	10	g/10 min	ASTM D1238
Molding Shrinkage			ASTM D955
Flow	2.6	%	ASTM D955
Transverse flow	4.1	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	5		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
100% strain	0.207	MPa	ASTM D412
200% strain	0.276	MPa	ASTM D412
300% strain	0.345	MPa	ASTM D412
Tensile Strength (Break)	2.07	MPa	ASTM D412
Tensile Elongation (Break)	700	%	ASTM D412
Tear Strength	7.01	kN/m	ASTM D624
Compression Set	34	%	ASTM D395
Injection	Nominal Value	Unit	
Rear Temperature	138 - 149	°C	
Middle Temperature	149 - 160	°C	
Front Temperature	160 - 171	°C	
Nozzle Temperature	171 - 182	°C	
Processing (Melt) Temp	171 - 182	°C	
Mold Temperature	21.1 - 37.8	°C	
Injection Pressure	1.38 - 5.52	MPa	

Back Pressure	0.172 - 0.689	MPa
Screw Speed	50 - 100	rpm
Cushion	3.81 - 25.4	mm

Injection instructions

Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C).

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

