

# Flexoprene® 65

Polyethylene

Puma Tecnica S.A.I.C.F.I

## Message:

Flexoprene® 65 is a Polyethylene product. It is available in Latin America. Typical application: Coating Applications.

Characteristics include:

Corrosion Resistant

Wear Resistant

General Information			
Features	Good Corrosion Resistance		
	Good Wear Resistance		
Uses	Coating Applications		
Physical	Nominal Value	Unit	Test Method
Density	1.10	g/cm <sup>3</sup>	ISO 1183
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	65		
Mechanical	Nominal Value	Unit	Test Method
Deformation Under Load	36.0	%	DIN 53517
Abrasion	65	mm <sup>3</sup>	DIN 53516
Rebound Resilience	37	%	DIN 53512
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			DIN 53504
100% Strain	22.0	MPa	
300% Strain	40.0	MPa	
Tensile Stress (Yield)	40.0	MPa	DIN 53504
Tensile Elongation (Break)	300	%	DIN 53504
Tear Strength	110	kN/m	DIN 53515

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT