

ISOTHANE® 2095A-M1

Thermoplastic Polyurethane Elastomer (Polycaprolactone)

Great Eastern Resins Industrial Co., Ltd. (GRECO)

Message:

ISOTHANE 2095A-M1 product is polycaprolactone based thermoplastic polyurethanes. It exhibits high elasticity, hydrolysis resistant, oil resistance and low compression set. This product is particularly suitable for oil seals production. The product can be injection molded.

Suggested Applications:

Gaskets, Oil Rings, Seals, Packing, Boots, Pads, Hoops, Tubes, Shoes.

General Information			
Features	Low compressive deformability		
	High elasticity		
	Hydrolysis resistance		
	Oil resistance		
	General		
Uses	Packaging		
	Washer		
	Pipe fittings		
	Seals		
	General		
	Footwear		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	94		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
50% strain	12.0	MPa	ASTM D412
100% strain	15.0	MPa	ASTM D412
300% strain	35.0	MPa	ASTM D412
Tensile Strength	56.0	MPa	ASTM D412
Tensile Elongation (Break)	390	%	ASTM D412
Tear Strength ¹	164	kN/m	ASTM D624
Compression Set			ASTM D395B
70°C, 24 hr	29	%	ASTM D395B
100°C, 24 hr	41	%	ASTM D395B
Bayshore Resilience	34	%	ASTM D2632
Injection	Nominal Value	Unit	

Rear Temperature	195 - 205	°C
Middle Temperature	200 - 210	°C
Front Temperature	200 - 210	°C
Nozzle Temperature	190 - 200	°C

NOTE

1.
- C mould

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT