

# Tecnoflon® T 938

Fluoroelastomer  
Solvay Specialty Polymers

Message:

TECNOFロン® T 938 is a medium viscosity fluoroelastomer terpolymer with 68.5% fluorine content. Tecnoflon® T 938 does not contain curatives: therefore the proper levels of Tecnoflon® FOR M1 and Tecnoflon® FOR M2 must be added to achieve the required properties. Tecnoflon® T 938 exhibits the chemical resistance typical of fluoroelastomer terpolymers. It is well suited for applications requiring better chemical resistance and/or long term heat resistance compared to fluoroelastomer copolymers. Some of the basic properties of TECNOFロン® T 938 are:  
Excellent chemical resistance  
Good heat resistance  
Very good processability  
Tecnoflon® T 938 can be used for compression, injection and transfer molding of shaft seals, valve stem seals, gaskets or any item requiring excellent chemical resistance  
This material can be combined with the cure system and other typical fluoroelastomer compounding ingredients. Mixing can be accomplished with two-roll mills or internal mixers. Tecnoflon® T 938 can be extruded into hoses or profiles and can be calendered to make sheet stocks or belting. Finished goods can be produced by a variety of rubber processing methods.

General Information	
Features	Good Chemical Resistance
	Good Heat Aging Resistance
	Good Processability
	High Heat Resistance
	Medium Viscosity
	Terpolymer
Uses	Belts/Belt Repair
	Blending
	Gaskets
	Hose
	Profiles
	Seals
	Sheet
	Valves/Valve Parts
Appearance	Translucent
Forms	Slab
Processing Method	Calendering
	Compounding
	Compression Molding
	Extrusion
	Injection Molding
	Resin Transfer Molding

Physical	Nominal Value	Unit
Mooney Viscosity <sup>1</sup> (ML 1+10, 121°C)	66	MU
Fluorine Content <sup>2</sup>	69	%
NOTE		
1.	Raw polymer	
2.	Raw polymer	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

