

Styropor® P 326 M

Expanded Polystyrene

BASF Corporation

Message:

Application

For the production of expanded foam moldings having a wall thickness of at least 8 mm with very good mechanical properties. Expanded foam made from Styropor ® 326 M exhibits mechanical properties which go beyond those of expanded foam made from P 326, especially with regard to flexural strength.

Product description

Expandable polystyrene (EPS) (blowing agent: pentane).

General Information		
Additive	Blowing Agent 2	
Uses	Foam	
Agency Ratings	EC 1907/2006 (REACH)	
RoHS Compliance	RoHS Compliant	
Forms	Spheres	
Physical	Nominal Value	Unit
Apparent Density	0.02	g/cm³
Sieve Analysis		
< 500.0 µm	< 2.0	%
500.0 to 1000.0 µm	> 93	%
> 1.00 mm	< 5.0	%
Aging - intermediate	10.0 to 24.0	hr
Bead Size	700.0 to 900.0	µm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT