

Greenflex® MQ 40

Ethylene Vinyl Acetate Copolymer

Versalis S.p.A.

Message:

Greenflex MQ 40 is an ethylene vinyl acetate copolymer (EVA) for injection moulding and compounding.

Greenflex MQ 40 combines high fluidity and high elasticity.

Main Application

Greenflex MQ 40 is recommended for injection moulding of gaskets, ski sticks rounds, foamed and crosslinked articles.

General Information			
Features	Copolymer		
	Crosslinkable		
	Foamable		
	Food Contact Acceptable		
	High Elasticity		
	High Flow		
Uses	Compounding		
	Foam		
	Gaskets		
	Sporting Goods		
Agency Ratings	EU Food Contact, Unspecified Rating		
Forms	Pellets		
Processing Method	Compounding		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.941	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	12	g/10 min	ISO 1133
Vinyl Acetate Content	19.0	wt%	Internal Method
Hardness	Nominal Value	Unit	Test Method
Shore Hardness			ISO 868
Shore A, Injection Molded	89		
Shore D, Injection Molded	33		
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield, Injection Molded)	4.00	MPa	ISO 527-2
Flexural Modulus (Injection Molded)	40.0	MPa	ISO 178
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	< -80.0	°C	ASTM D746

Vicat Softening Temperature	56.0	°C	ISO 306/A
Melting Temperature	83.0	°C	Internal Method
Injection	Nominal Value	Unit	
Processing (Melt) Temp	140 to 200	°C	
Mold Temperature	10.0 to 30.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

