

Durethan® ECO BKV 20 FN20 000000

Polyamide 6

LANXESS GmbH

Message:

PA 6, 20 % glass, injection molding, halogen free flame retardant, contains at least 15 % pre-consumer-recyclate

General Information				
Filler / Reinforcement	Glass fiber reinforced material, 20% filler by weight			
Additive	Flame retardancy			
Recycled Content	Yes, 15%			
Features	Halogen-free			
	Flame retardancy			
Agency Ratings	EC 1907/2006 (REACH)			
Processing Method	Injection molding			
Resin ID (ISO 1043)	PA G FR (30)			
Physical	Dry	Conditioned	Unit	Test Method
Density (23°C)	1.31	--	g/cm ³	ISO 1183
Apparent Density	0.70	--	g/cm ³	ISO 60
Molding Shrinkage				ISO 2577
Vertical flow direction: 260°C, 2.00mm ¹	0.80	--	%	ISO 2577
Vertical flow direction: 120°C, 4 hours, 2.00mm ²	0.20	--	%	ISO 2577
Flow direction: 260°C, 2.00mm ³	0.80	--	%	ISO 2577
Flow direction: 120°C, 4 hours, 2.00mm ⁴	0.20	--	%	ISO 2577
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	5400	2300	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	76.0	40.0	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	3.0	27	%	ISO 527-2/5
Flexural Modulus ⁵ (23°C)	5300	2300	MPa	ISO 178/A
Flexural Stress				ISO 178/A
3.5% strain, 23°C	135	50.0	MPa	ISO 178/A
23°C ⁶	140	62.0	MPa	ISO 178/A
Flexural Strain at Flexural Strength ⁷ (23°C)	3.8	7.0	%	ISO 178/A
ISO Shortname	PA 6, GFHR, 12-050, G20	--		ISO 1874
Admissible Residence Time at Tmax			min	
Residual Moisture Content	0.030 - 0.070		%	Karl Fisher

Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	< 10	< 10	kJ/m ²	ISO 179/1eA
23°C	< 10	< 10	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	35	75	kJ/m ²	ISO 179/1eU
Notched Izod Impact				ISO 180/1A
-30°C	< 10	< 10	kJ/m ²	ISO 180/1A
23°C	< 10	< 10	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength (23°C)	30	65	kJ/m ²	ISO 180/1U
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, not annealed	210	--	°C	ISO 75-2/B
1.8 MPa, not annealed	155	--	°C	ISO 75-2/A
Vicat Softening Temperature	205	--	°C	ISO 306/B120
Ball Pressure Test (209°C)	Pass	--		IEC 60695-10-2
Melting Temperature ⁸	222	--	°C	ISO 11357-3
Linear thermal expansion coefficient				ISO 11359-2
Flow: 23 to 55°C	5.0E-5	--	cm/cm/°C	ISO 11359-2
Lateral: 23 to 55°C	8.0E-5	--	cm/cm/°C	ISO 11359-2
Electrical	Dry	Conditioned	Unit	Test Method
Dielectric Strength (23°C, 1.00 mm)	32	--	kV/mm	IEC 60243-1
Comparative Tracking Index (CTI)	PLC 0	--		UL 746
Comparative Tracking Index (Solution A)	600	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
0.750 mm	V-2	--		UL 94
1.50 mm	V-2	--		UL 94
3.00 mm	V-2	--		UL 94
Glow Wire Flammability Index				IEC 60695-2-12
0.800 mm	960	--	°C	IEC 60695-2-12
1.50 mm	960	--	°C	IEC 60695-2-12
3.00 mm	960	--	°C	IEC 60695-2-12
Oxygen Index ⁹	30	--	%	ISO 4589-2
Injection	Dry	Unit	Test Method	
Drying Temperature - Dry Air Dryer	80.0		°C	

Drying Time - Dry Air Dryer	2.0 - 6.0	hr
Processing (Melt) Temp	250 - 270	°C
Mold Temperature	80.0 - 100	°C

NOTE		
1.	60x60x2mm, 80°C MT, 600 bar	
2.	60x60x2mm	
3.	60x60x2mm, 80°C MT, 600 bar	
4.	60x60x2mm	
5.	2.0 mm/min	
6.	2.0 mm/min	
7.	2 mm/min	
8.	10°C/min	
9.	Procedure A	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT