

# LUVOCOM® 50-0833

Polycarbonate

Lehmann & Voss & Co.

## Message:

LUVOCOM® 50-0833 is a polycarbonate (PC) material, which contains glass and carbon fiber reinforced materials. This product is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific.

LUVOCOM® The main features of 50-0833 are:

Conductivity

Electrostatic protection

Good dimensional stability

Typical application areas include:

engineering/industrial accessories

business/office supplies

Sporting goods

medical/health care

General Information			
Filler / Reinforcement	Glass, carbon fiber reinforced materials		
Features	Good dimensional stability		
	Conductivity		
	Electrostatic discharge protection		
Uses	Gear		
	Engineering accessories		
	Business equipment		
	Sporting goods		
	Medical/nursing supplies		
Appearance	Black		
Physical	Nominal Value	Unit	Test Method
Density	1.33	g/cm <sup>3</sup>	ISO 1183
Molding Shrinkage	0.20 - 0.50	%	DIN 16901
Water Absorption (23°C, 24 hr)	< 0.20	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	9500	MPa	ISO 527-2
Tensile Stress (Break)	125	MPa	ISO 527-2
Tensile Strain (Yield)	2.2	%	ISO 527-2
Flexural Modulus	8000	MPa	ISO 178
Flexural Stress	185	MPa	ISO 178
Coefficient of Friction			
Dynamic	0.24		
Static	0.22		
Flexural Strain at Flexural Strength	3.0	%	ISO 178

Maximum operating temperature-Short Term	150	°C	
Insulation Resistance		ohms	IEC 60167
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	130	°C	UL 746B
Vicat Softening Temperature	160	°C	ISO 306/A
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	< 1.0E+3	ohms	IEC 60093
Injection	Nominal Value	Unit	
Drying Temperature	120	°C	
Drying Time	4.0 - 6.0	hr	
Suggested Max Moisture	0.020	%	
Rear Temperature	280 - 300	°C	
Middle Temperature	290 - 310	°C	
Front Temperature	300 - 320	°C	
Nozzle Temperature	290 - 310	°C	
Processing (Melt) Temp	295	°C	
Mold Temperature	80.0 - 120	°C	
Injection instructions			

#### General

In general LUVOCOM® can be processed on conventional injection moulding machines while observing the usual technical guidelines. Any added fibrous materials or fillers may have an abrasive effect. In this case the cylinder and screw should be protected against wear as is usual in the processing of reinforced thermoplastic materials. Lengthy dwell times for the melts in the cylinder should be avoided.

Lower the temperatures during interruptions!

#### Predrying (optional)

It is advisable to predry the granulate with a suitable dryer immediately before processing.

The granulate may absorb moisture from the air.

#### Delivery Form & Storage

Unless indicated otherwise, the material is delivered as 3mm-long pellets in sealed bags on pallets.

Preferably storage should be effected in dry and normally temperatured rooms

#### Additional Information

During processing, the moisture level should not exceed 0.02%, otherwise molecular degradation may occur.

Suitable heat treatment may increase resistance to the formation of stress cracks.

The processing notes provided merely represent a recommendation for general use. Due to the large variety of machines, geometries and volumes of parts, etc., it may be necessary to employ different settings according to the specific application.

Please contact us for further information.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT