

Ipethene® 600

Low Density Polyethylene

Carmel Olefins Ltd.

Message:

IPETHENE ® 600 is a low density polyethylene injection molding grade, produced by high pressure autoclave technology. It is a medium MFR grade with good flow properties and good stiffness.

General Information			
Features	Good Flow		
	Good Stiffness		
	Low Density		
Uses	Containers		
	Cups		
	Household Goods		
	Lids		
	Masterbatch		
	Toys		
Agency Ratings	EC 1907/2006 (REACH)		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.917	g/cm ³	ISO 1183/A
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	7.0	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	45		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break)	11.0	MPa	ISO 527-2
Tensile Strain (Break)	90	%	ISO 527-2
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	90.0	°C	ISO 306
Melting Temperature ¹	107	°C	ISO 11357-3
Injection	Nominal Value	Unit	
Processing (Melt) Temp	160 to 220	°C	
Mold Temperature	10.0 to 40.0	°C	
NOTE			
1.	By DSC		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

