

ZEONOR® 1430R

Cyclo Olefin Polymer

Zeon Corporation

Message:

High flow, high transparency, low fluorescence grade for light guide and diagnostic consumable

Features

High transparency

Low fluorescence

Low moisture absorption

Very low extractable

High purity

Uses

Light guide

Diagnostic consumable

Microfluidic

Mirror

General Information			
Features	High purity		
	Low extract		
	Low hygroscopicity		
	High liquidity		
	Definition, high		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS compliance		
Appearance	Clear/transparent		
Processing Method	Blow molding		
	Extrusion		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.01	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (280°C/2.16 kg)	30	g/10 min	JIS K6719
Water Absorption (Equilibrium)	< 0.010	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2300	MPa	ISO 527-2
Tensile Stress	60.0	MPa	ISO 527-2
Tensile Strain (Break)	16	%	ISO 527-2
Flexural Modulus	2200	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	25	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method

Glass Transition Temperature	136	°C	JIS K7121
CLTE - Flow	7.0E-5	cm/cm/°C	ASTM E831
Electrical	Nominal Value		Test Method
Dielectric Constant (1.00 GHz)	2.30		ASTM D150
Dissipation Factor (1.00 GHz)	< 1.0E-3		ASTM D150
Optical	Nominal Value	Unit	Test Method
Transmittance (3000 μm)	92.0	%	ASTM D1003

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

