

# Trademark PP PPC2040M

Polypropylene Impact Copolymer

Trademark Plastics Corporation

## Message:

Trademark PP PPC2040M is a Polypropylene Impact Copolymer (PP Impact Copolymer) product. It can be processed by compounding or injection molding and is available in North America. Applications of Trademark PP PPC2040M include additive/masterbatch, automotive, caps/lids/closures, food contact applications and household applications.

Characteristics include:

- Copolymer
- Food Contact Acceptable
- Good Adhesion
- Good Processability
- Impact Resistant

General Information			
Features	Food Contact Acceptable		
	Good Adhesion		
	Good Color Stability		
	Good Processability		
	High Impact Resistance		
	Impact Copolymer		
Uses	Automotive Applications		
	Closures		
	Compounding		
	Household Goods		
	Sporting Goods		
Agency Ratings	FDA 21 CFR 177.1520		
Processing Method	Compounding		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.900	g/cm <sup>3</sup>	ASTM D1505
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	20	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength <sup>1</sup> (Yield)	21.4	MPa	ASTM D638
Tensile Elongation <sup>2</sup> (Yield)	6.0	%	ASTM D638
Flexural Modulus	1010	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	210	J/m	ASTM D256
NOTE			

1.	51 mm/min
2.	51 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

