

PERLER® N09X2500B00

Polypropylene Homopolymer

A.D. Compound S.p.A.

Message:

PP Homopolymer Natural 25% Mixed Mineral filled

General Information			
Filler / Reinforcement	Mineral filler, 25% filler by weight		
Features	Homopolymer		
Appearance	Natural color		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	27	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus	1800 - 2100	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	2.0 - 4.0	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	98.0	°C	ISO 306
Heat Deflection Temperature	54	°C	ISO 75-2

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT