

# TechnoFin MA 80

Polypropylene  
TechnoCompound GmbH

Message:  
TechnoFin compounds with variable flow behaviour, good workability, possess good damping characteristics, high rigidity and very good abrasion behaviour.

General Information			
Filler / Reinforcement	Magnetite filler, 80% filler by weight		
Features	Rigidity, high		
	Impact resistance, good		
	Good wear resistance		
Uses	Plug		
	Gear		
	Electrical/Electronic Applications		
	Electrical housing		
	Electrical appliances		
	Furniture		
	Household goods		
	Parts under the hood of a car		
	Application in Automobile Field		
	Car interior parts		
	Shell		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	3.10	g/cm <sup>3</sup>	ISO 1183
Additional Information			
Moisture Content, Infared 105°C, 15 min: <0.10%Ash Content, ISO 3451, 950°C: 80%			
Injection	Nominal Value	Unit	
Processing (Melt) Temp	220 - 270	°C	
Mold Temperature	30.0 - 90.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

