

RTP 1399 X 115071 C

Polyphenylene Sulfide

RTP Company

Message:

Glass Fiber - Carbon Nanotube - ESD Protection

General Information			
Filler / Reinforcement		Carbon Nano Glass Fiber	
Features		ESD Protection	
RoHS Compliance		Contact Manufacturer	
Processing Method		Injection Molding	
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.60	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.20 mm)	0.20 to 0.30	%	ASTM D955
Moisture Content	0.040	%	
Static Decay	< 2.0	sec	FTMS 101C 4046.1
Primary Additive	30	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	13800	MPa	ASTM D638
Tensile Strength	131	MPa	ASTM D638
Tensile Elongation (Yield)	1.0	%	ASTM D638
Flexural Modulus	12400	MPa	ASTM D790
Flexural Strength	207	MPa	ASTM D790
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity			
--	1.0E+3 to 1.0E+4	ohms	ASTM D257
--	1.0E+2 to 1.0E+3	ohms	ESD STM11.11
Volume Resistivity	< 1.0E+2	ohms · cm	ASTM D257
Injection	Nominal Value	Unit	
Drying Temperature	149	°C	
Drying Time	6.0	hr	
Processing (Melt) Temp	307 to 329	°C	
Mold Temperature	135 to 177	°C	
Injection Pressure	68.9 to 103	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

