

Hyundai EP PA66 LD380

Polyamide 66
HYUNDAI EP Co., Ltd.

Message:
Hyundai EP PA66 LD380 is a Polyamide 66 (Nylon 66) product filled with 40% glass fiber. It is available in Asia Pacific. Primary characteristic: heat stabilizer.

General Information			
Filler / Reinforcement	Glass Fiber,40% Filler by Weight		
Additive	Heat Stabilizer		
Features	General Purpose		
	Heat Stabilized		
Uses	General Purpose		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	1.49	g/cm ³	ASTM D1505
Molding Shrinkage - Flow	0.30 to 0.60	%	ASTM D955
Ash Content	40	%	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	121		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	167	MPa	ASTM D638
Tensile Elongation (Break)	5.0	%	ASTM D638
Flexural Modulus	8340	MPa	ASTM D790
Flexural Strength	226	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	49	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	230	°C	ASTM D648
Melting Temperature	265	°C	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+13 to 1.0E+15	ohms · cm	ASTM D257
Dielectric Strength	3.5	kV/mm	ASTM D149

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

