

Chemlon® 133 GU

Polyamide 66

Teknor Apex Company (Chem Polymer)

Message:

Chemlon® 133 GU is a Polyamide 66 (Nylon 66) material filled with 33% glass fiber. It is available in Asia Pacific, Europe, or North America for injection molding.

Important attributes of Chemlon® 133 GU are:

High Strength

Impact Resistant

UV Stabilized

General Information			
Filler / Reinforcement	Glass Fiber,33% Filler by Weight		
Additive	UV Stabilizer		
Features	Good Impact Resistance		
	High Tensile Strength		
Appearance	Natural Color		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.38	g/cm ³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	176	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	2.0	%	ASTM D638
Flexural Modulus (23°C)	8270	MPa	ASTM D790
Flexural Strength (23°C)	241	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	110	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	249	°C	ASTM D648
Melting Temperature	254	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

