

RTP 2581 FR

Polycarbonate + ABS

RTP Company

Message:

Warning: The status of this material is 'Commercial: Limited Issue'
The data for this material has not been recently verified.
Please contact RTP Company for current information prior to specifying this grade.
RTP 2581 FR Series materials are carbon fiber PAN reinforced polycarbonate/ABS alloy. These materials meet the flammability requirements of UL94 V-0 and are available in a range of colors. They are characterized with excellent physical properties and improved process.

General Information			
Filler / Reinforcement	Carbon Fiber,10% Filler by Weight		
Additive	Flame Retardant		
Features	Flame Retardant		
	Good Processability		
RoHS Compliance	Contact Manufacturer		
Appearance	Black		
	Colors Available		
	Natural Color		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.24	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.20	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.10	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	8620	MPa	ASTM D638
Tensile Strength	124	MPa	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus	7580	MPa	ASTM D790
Flexural Strength	172	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm)	110	J/m	ASTM D256
Unnotched Izod Impact (3.18 mm)	480	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	107	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+5	ohms · cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method

Flame Rating (1.59 mm, RTP Tested)	V-0	UL 94
Injection	Nominal Value	Unit
Drying Temperature	98.9	°C
Drying Time	4.0	hr
Suggested Max Moisture	0.020	%
Suggested Max Regrind	20	%
Rear Temperature	232 to 288	°C
Middle Temperature	232 to 288	°C
Front Temperature	232 to 288	°C
Mold Temperature	71.1 to 98.9	°C
Injection Pressure	68.9 to 103	MPa
Back Pressure	0.345	MPa
Clamp Tonnage	6.9 to 11	kN/cm ²

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

