

SLOVALEN® EQ 71 N

Low Density Polyethylene + EVA

Plastcom

Message:

PE modified with EVA. The addition of EVA causes increased impact strength. General application in all industry branches. Delivered in natural mode and in the full RAL colour scale.

General Information			
Features	General Purpose		
	Good Impact Resistance		
Uses	General Purpose		
Appearance	Colors Available		
	Natural Color		
Processing Method	Injection Molding		
Resin ID (ISO 1043)	PP+EVA		
Physical	Nominal Value	Unit	Test Method
Density	0.930	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	25	g/10 min	ISO 1133
Molding Shrinkage			STM 64 0808
Across Flow	3.0	%	
Flow	2.5	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	950	MPa	ISO 527-2
Tensile Stress (Yield)	20.0	MPa	ISO 527-2
Tensile Strain (Yield)	400	%	ISO 527-2
Flexural Modulus	950	MPa	ISO 178
Flexural Stress	25.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-20°C	45	kJ/m ²	
23°C	No Break		
Charpy Unnotched Impact Strength			ISO 179
-20°C	No Break		
23°C	No Break		
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	45.0	°C	ISO 75-2/B
Vicat Softening Temperature	75.0	°C	ISO 306/B

Melting Temperature (DSC)	120	°C	ISO 3146
Injection	Nominal Value	Unit	
Drying Temperature	70.0	°C	
Drying Time	2.0	hr	
Processing (Melt) Temp	170 to 220	°C	
Mold Temperature	30.0 to 50.0	°C	
Injection Pressure	50.0 to 80.0	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

