

PRL TP-GP2

Polybutylene Terephthalate

Polymer Resources Ltd.

Message:

PRL TP-GP2 is a Polybutylene Terephthalate (PBT) product. It can be processed by injection molding and is available in North America.

Characteristics include:

Flame Rated

RoHS Compliant

General Information			
UL YellowCard	E113219-219237		
Features	General Purpose		
RoHS Compliance	RoHS Compliant		
UL File Number	E113219		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.31	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (250°C/2.16 kg)	12 to 20	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.18 mm)	1.6 to 2.2	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield, 3.18 mm	51.7	MPa	
Break, 3.18 mm	51.7	MPa	
Flexural Modulus (3.18 mm)	2310	MPa	ASTM D790
Flexural Strength (Break, 3.18 mm)	79.3	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	53	J/m	ASTM D256
Gardner Impact (3.18 mm)	36.2	J	ASTM D3029
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, 3.18 mm	149	°C	
1.8 MPa, Unannealed, 3.18 mm	60.0	°C	
RTI Elec			UL 746
1.50 mm	130	°C	
3.00 mm	130	°C	
RTI Imp			UL 746
1.50 mm	120	°C	
3.00 mm	120	°C	
RTI Str			UL 746

1.50 mm	130	°C	
3.00 mm	130	°C	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+14	ohms·cm	ASTM D257
Dielectric Strength (1.50 mm)	30	kV/mm	ASTM D149
Arc Resistance (1.50 mm)	PLC 5		ASTM D495
Comparative Tracking Index (CTI) (1.50 mm)	PLC 0		UL 746
High Amp Arc Ignition (HAI)			UL 746
1.50 mm	PLC 0		
3.00 mm	PLC 0		
High Voltage Arc Tracking Rate (HVTR) (1.50 mm)	PLC 1		UL 746
Hot-wire Ignition (HWI)			UL 746
1.50 mm	PLC 3		
3.00 mm	PLC 3		
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.50 mm	HB		
3.00 mm	HB		
Injection	Nominal Value	Unit	
Drying Temperature	116 to 121	°C	
Drying Time	3.0 to 4.0	hr	
Drying Time, Maximum	8.0	hr	
Rear Temperature	232 to 249	°C	
Middle Temperature	238 to 254	°C	
Front Temperature	243 to 260	°C	
Processing (Melt) Temp	232 to 260	°C	
Mold Temperature	43.3 to 76.7	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT